1. Identification of the Substance/Mixture and of the Company/Undertaking

1.1. Product identifier

Form of the product Mixture/Fibre

Product name Wiking® Fibre

Customs Tariff No. 55.03.40.00

Chemical name Polypropylene: (C3H6)x

Product type Polypropylene Homopolymer – PPH

1.2. Relevant, identified uses of the substance or mixture and uses advised.

1.2.1 Relevant identified uses

Main use category Commercial use

Relevant identified For more detailed information, see product data sheet

uses of the substance

1.2.2 Uses that are advised against

Main Food products

1.3. Details of the supplier of the safety data sheet

Danish Fibres A/S Snedkervej 3 DK 6800 Varde Denmark T +45 88389890 info@danishfibres.dk www.danishfibres.dk

2. Hazards Identification

2.1. Classification of the substance or mixture

The product in the form of granules is not classified as hazardous pursuant to provisions set forth in EC Regulation 1272/2008 (CLP) (and subsequent amendments and supplements), nor it requires an SDS according to Article 31 of Regulation (EC) 1907/2006 (REACH).

The product marketed in the form of film is considered "article" under REACH (Reg. (EC) 1907/2006), therefore it is not subject to the obligation of the safety data sheet (Article 31 of the REACH Reg.), neither classification and labeling in accordance with Regulation 1272/2008 (CLP).

2.2. Label elements

Hazard pictograms:NoneSignal words:NoneHazard statements:NonePrecautionary statements:None



2.3. Other hazards

On the basis of available data, the product does not contain any PBT or vPvB in percentage greater than 0,1%.

Physical-chemical, health and environmental effects To the best of Danish Fibres A/S's knowledge, this product does not present any particular risk, provided that general rules for occupational hygiene are observed.

Other hazards which do not contribute to classification

Contact with hot product - risk of serious burns. Vapours or fumes may form at temperatures exceeding 160°C; these can irritate the respiratory tract, resulting in coughing and shortness of breath. Handling the product can generate build-up of

static electricity. Use appropriate earthing methods.

Physical-chemical hazards Flammable in the presence of flames.

Composition/Information on Ingredients

3.1. Substances

Information not relevant.

3.2. Mixtures

Propylene homopolymers (Cas no. 9003-07-0) > 98% Not classified

Spin oil <2% Symptoms

the respiratory

If the product is heated to more than 235°C, vapours can form and they can irritate

associated with inhalation tract, resulting in coughing and a feeling of breathlessness.

Polypropylene antioxidants and stabilizers: max 2.0%

The Wrap film used on Polypucks products is mainly made of fully- and/or partially-hydrolyzed polyvinyl alcohol (CAS 9002-89-5; 25213-24-5); other components fall within the category of polyol plasticizers and process additives of organic and inorganic nature.

First Aid Measures

Inhalation Fresh air.

Contact with skin Wash the affected areas with cold water. Consult a dermatologist if necessary.

Contact with eyes least 10 minutes). If there is any irritation, wash with plenty of water until the irritation resolves (at

Consult an ophthalmologist if necessary.

Ingestion Ingestion during handling is unlikely. Ingestion of small quantities has no

significant effects. Ingestion of large amounts can cause abdominal pain and

diarrhoea. Consult a physician if necessary.

4.1. Description of first aid measures on PVA Film

Not specifically necessary. Observance of good industrial hygiene is recommended.

4.2. Most important symptoms and effects, both acute and delayed

No episodes of damage to health ascribable to the product have been reported.

4.3. Indication of any immediate medical attention and special treatment needed

None



5. Firefighting Measures

Technical Measures Stop the fire spreading. Call the fire brigade immediately. Evacuate nonessential

personnel.

Protective clothing, goggles and self-contained breathing equipment should be

made available for firemen.

Extinguishing Media For minor fires: carbon dioxide or powder for more extensive fires: foam.

Suitable Water spray (mist) to cool the surfaces exposed to the fire.

Not to be used: Do not use water jets (stick jets) in the early stages of

extinguishing fire since they could help to spread the flames.

Combustion Products

vapour.

aldehydes,

Complete combustion, with an excess of oxygen forms: carbon dioxide and water

Partial combustion also forms carbon monoxide, soot, and segregated products:

ketones, hydrocarbons and volatile fatty acids.

5.1. Special hazards arising from the PVA Film or mixture.

HAZARDS CAUSED BY EXPOSURE IN THE EVENT OF FIRE

Do not breathe combustion products.

6. Accidental Release Measures

Fibres spilled on the floor should be recovered by sweeping or suction and put in containers to facilitate its disposal.

6.1. Personal precautions, protective equipment, and emergency procedures

Use breathing equipment if fumes or powders are released into the air. These indications apply for both processing staff and those involved in emergency procedures.

6.2. Environmental precautions

Avoid discharge into drains, water courses or onto the ground.

6.3. Methods and material for containment and cleaning up

Confine using earth or inert material. Collect as much material as possible and eliminate the rest using jets of water. Contaminated material should be disposed of in compliance with the provisions set forth in point 13.

6.4. Reference to other sections

Any information on personal protection and disposal is given in sections 8 and 13.



7.1. Do not store near highly flammable materials. Store away from heating source. Store in dry area to avoid degradation of the boxes and bags.

Storage Temperature < 100°C, > - 40°C.

Shelf Life One year.

7.2. Precautions for safe handling While using the PVA Film

Before handling the product, consult all the other sections of this material safety data sheet. Avoid leakage of the product into the environment. Do not eat, drink, or smoke during use.

Make sure that the operator's hands are dry when handling. The product tends to reach the hygrometric balance with the surrounding environment, or to absorb the humidity of the environment where it is located. The product characteristics are strongly influenced by the amount of moisture absorbed.

7.3. Conditions for safe storage, including any incompatibilities.

Keep the product in clearly labelled containers. Keep containers away from any incompatible materials, see section 10 for details.

PVA Film products must be stored in dry, ventilated places where the temperature is kept at 20±10°C and the relative humidity is kept at 40±10%. Temperature and humidity variations should be minimized to prevent shrinkage/deformation; the products must not get in contact with water or wet items as well as with any dissolving or reacting substance. The products must be used within 6 months from the delivery date.

The supplied product packaging must be kept intact until use. The best product performances are guaranteed with 40 ± 5 % of relative humidity and with a film temperature of 23 ± 2 °C. If some film is leftover on the reel, or not in use during the operation, it should be repacked with the original packaging to maintain intact the product properties.

7.4. Specific end use(s)

Polypucks for Concrete giving a better environmental.

8. Exposure Controls and Personal Protection

Occupational Exposure Limit Restorable dust particles not considered to be a hazard.

Personal Protection - Respiratory Protection

In case of risk of overexposure to dust, vapour, or fumes, it is recommended that a local exhaust system is placed above the conversion equipment, and the working area must be properly ventilated.

8.1. Control parameters By using PVA Film

Information not available.

8.2. Exposure controls

Comply with the safety measures usually applied when handling chemical substances.

General industrial hygiene practice. Because of the significant hygroscopic characteristic of the material, when brought to the plasticizing temperature (about 130°), it releases a certain amount of water vapor that can also develop at the exit of the machines such as the extrusion die as well as the packaging machine. The water vapor can also drag with it small amounts of plasticizers polyol contained in the material. In order to avoid condensation of fumes and vapors in the work environment, in compliance with the environmental hygiene standards, it is recommended the use of appropriate aspirators placed close to the emission source. Aspirated fumes and vapors can be condensed through water traps or dispersed outdoor if the local regulations permit. The amount of the emitted vapors may reach 3% of the weight of the extruded product.



Hand protectionNone required.Skin protectionNone required.Eye protectionNone required.

Respiratory protection None required, unless indicated otherwise in the chemical risk assessment.

Environmental The emissions generated by manufacturing processes, including those generated by ventilation equipment, should be checked to ensure compliance with environ-

mental standards.

9. Physical and Chemical Properties

Appearance Long monofilament or fibrillated fibre strands.

Physical State at 20℃ Solid.

Colour Translucent or white opaque odourless.

Odourless.

Change in Physical State at 1013 hPa

Melting Range (°C): From 160 to 165

Flash Point \pm 350.

(ASTM D 1929) (°C):

Auto-ignition > 380.

Temperature (°C):

Explosion Limits (kg/m³)

Lower: 0.020 (for polymer dust < 63 pm)

Min. ignition Energy at 20°C (mJ)

Density, mass at 20° C (kg/m³):

905 (ISOI183)

Solubility in Water

(%weight):

Insoluble.

Viscosity (mm²/s): Non-applicable.

Content of Chloride: < 0.001%

Density: 0.905 g/m³.

9.1. Information on basic physical and chemical properties using PVA Film

Appearance Solid (film or granules)

Colour White to light yellow; colored on request

Odour Slight acetic acid odor

Odour threshold Not available рΗ Not available Melting point / freezing point Not available Initial boiling point Not applicable Boiling range Not available Flash point Not applicable Evaporation rate Not available Flammability of Not available solids and gases



Lower inflammability limit Not available Upper inflammability limit Not available Lower explosive limit Not available Upper explosive limit Not available Vapour pressure Not available Vapour density Not available Relative density 1,15 - 1,35 g/cm3 Solubility Soluble in water Partition coefficient: Not available n-octanol/water

Auto-ignition temperatureNot availableDecomposition temperatureNot availableViscosityNot availableExplosive propertiesNot explosive

9.2. Reference to other sections

Information not available.

10. Stability and Reactivity

Stability Stable under normal operating conditions.

Conditions to avoid exceeding 300°C.

Avoid proximity or contact with flames or sparks. Do not heat to temperatures

10.1. Conditions to avoid while using PVA Film

Contact with flames and strong oxidizing agents. Exposure to direct sunlight can affect the quality of the product.

Temperature and humidity variations should be minimized in order to prevent shrinkage/deformation; the products must not get in contact with water or wet items as well as with any dissolving or reacting substance.

10.2. Incompatible materials while using PVA Film

Strong oxidizing agents. Avoid contact with components that may negatively affect the product's solubility :Borates; Cupric salts; Aluminium and Zinc salts; Titanium salts and Esters; Chromates, Dichromates, Vanadates; Germanates; Tripolyphosphates, Sodium phosphate; Sodium metasilicates; Isocyanuric acid; Sodium sulfate; Sodium hypochlorite; Dicarboxylic acids; isocyanates; Anhydrides (e.g. Tetrahydrophthalic anhydride); Aromatic aldehydes; Acetaldehyde, Butyraldehyde, Benzaldehyde, Glyoxal and Glutaraldehyde; Chloroaldehydic acids; Formamide and Dimethylformamide; Catechol, Resorcinol and derivatives.



11. Toxicological Information

Acute toxicity

Symptoms related to Use:

Inhalation Low risk for temperatures below 40°C. If heated to more than 235°C the product

may form vapours or fumes which may cause irritation of respiratory tract and

cause coughing and sensation of

shortness of breath.

Skin Contact thermal burns.

Eye Contact

No risk for temperatures below 40oC. Contact with hot material may cause severe

Fine dust may cause irritation to ocular mucous, splashing of molten droplets

causes ocular tissue injury.

Ingestion Minimal toxicity.

Carcinogenicity (mg/kg) IARC (International Agency on Research on Cancer): Category 3:

The agent is not classifiable as to its carcinogenicity to humans

Mutagenicity This product has been found to be non-mutagenic as well as non-genotoxic.

Other Polyolefins are biologically inert.

11.1. Information on toxicological effects While using PVA Film

According to currently available data, this product has not yet produced health damages. Anyway, it must be handled according to good industrial practices.

12. Ecological Information

Information on

Ecological Effects

Avoid losses to the environment whenever possible.

Mobility:

Air There is a slow loss by evaporation.

Soil Because of its physicochemical properties, the product generally has low soil mo-

bility.

Water Because of its low solubility the product should not be dangerous for aquatic life.

Persistence and Degradability Persistent in the environment.

Biodegradation This substance is slowly biodegradable.

Bio accumulative Potential Potential

Use this product according to good working practices.

While using PVA Film

12.1. Toxicity

Information not available.

12.2. Persistence and degradability

The product tends to degrade (conversion to carbon dioxide, water and cellular biomass) in aqueous environments (industrial and domestic effluent, water from river and sea surface) in a relatively short time.



12.3. Bio accumulative potential

Information not available.

12.4. Mobility in soil

Information not available.

12.5. Results of PBT and vPvB assessment

Based on available data, the product does not contain any PBT or vPvB in percentage greater than 0,1%.

12.6. Other adverse effects

Information not available.

13. Disposal Considerations

Disposal According to local regulations. Can be disposed of as refuse for reprocessing.

Do not dispose of by means of sinks, drains or into the immediate environment.

It may be used as fuel in suitably designed installations.

14. Transport Information

No restriction on transport by road, water, rail, or flight.

15. Regulatory information

Labelling

No labelling is required in accordance with the EEC directives.

15.1. Safety, health, and environmental regulations/legislation specific for the substance or mixture while using the PVA Film

Seveso category None

Restrictions relating to the product or contained substances pursuant to Annex XVII to EC Regulation 1907/2006 None

Substances in Candidate List (Art. 59 REACH) None

Substances subject to authorization (Annex XIV REACH) None

Substances subject to exportation reporting pursuant to (EC) Reg. 649/2012 None

Substances subject to the Rotterdam Convention None

Substances subject to the Stockholm Convention None.

Healthcare controls Information not available

German regulation on the classification of substances hazardous to water (VwVwS 2005). WGK 1: Low hazard to waters

15.2. Chemical safety assessment

No chemical safety assessment has been processed for the mixture and the substances it contains.





16. Other information

Danish Fibres documents, including all drawings, proposed procedures and specifications are exclusively general information.

Details can be changed without prior warning. Practical application of the information requires independent, professional consul-tansy and verification of its precision, suitability and usability. The user alone shall be liable for the actual application of the products, including the choice of product, the use, the design, the production, or the test of the materials in which our products are used.

Danish Fibres shall not be held liable for the end products or for the use of our products.

Danish Fibres shall in no case be liable for any damage, including direct or indirect losses that might occur as a consequence of wrong application of the information. See also the general sales and delivery terms from Danish Fibres.

