

Technical Fibres 16 micron

Product specification

Wiking® Technical Fibres are all-round fibres developed for use in needle felts, filters and other technical applications. They are made of polypropylene and have a number of unique properties, which explain their growing popularity in technical end uses.

Density

Wiking® Technical Fibres are the lightest of all fibres and can therefore produce equivalent products (with same area coverage) using less weight of fibres.

Comparison of fibre densities (g/cm³)

| | |
|-------------------|------|
| Polypropylene | 0.91 |
| Polyester | 1.38 |
| Amide | 1.44 |
| Polyacrylonitrile | 1.18 |
| Viscose/Rayon | 1.51 |
| Wool | 1.32 |
| Cotton | 1.54 |

Thermal properties

Wiking® Technical Fibres have very low thermal conductivity, which makes them excellent insulators against heat, sound and electrostatic charge.

This is the lowest moisture absorption of all fibres and therefore quick drying is guaranteed.

Specifications - Wiking® Technical Fibres 16 micron

| | |
|---|------------------------|
| Tensile strength | 2.5-8.0 cN/dtex |
| Elongation | 30-180% |
| Crimp/10 cm | 50-70 curves |
| If textures: | |
| Shrinkage - At 130°C/10 minutes | <3-4% |
| Max. Fixation Temperature | 130°C |
| Softening Temperature | 150°C |

2026.01.26



| | |
|--|------------|
| Softening point | 140-150°C |
| Melting range | 165° C<3% |
| Thermal shrinkage - (hot air 10 min/130 °C) | <3% |
| Processing- temperature | max. 130°C |
| Absorption Wiking® Technical Fibres do not absorb water | |
| Moisture absorption - at 20°C/65% R.H. | 0,05% |
| Water absorption | <0,1% |

At the same time, Wiking® Technical Fibres in Tow have the same tensile strength, whether wet or dry, unlike most other fibres.

Comparison of wet tensile strength in % of original strength:

| | |
|-------------------|----------|
| Polypropylene | 100% |
| Polyester | 100% |
| Polyamide | 80-90% |
| Polyacrylonitrile | 85-95% |
| Viscose/Rayon | 50-60% |
| Wool | 80-90% |
| Cotton | 100-110% |

Chemical and biological resistance

All Wiking® Technical Fibres in Tow are highly resistant to both acids and alkalis and to more organic chemicals.

Moreover, they do not rot and are not attacked by insects, micro organisms or moulds.

Light and heat resistance

Wiking® Technical Fibres in Tow can be specially treated with UV-stabilizers during manufacturing to obtain resistance against the effect of UV in sunlight.

Electrostatic behaviour

Wiking® Technical Fibres in Tow have very little tendency to acquire static

charge. The antistatic property of these fibres is even superior to that of polyamide and wool.

Product range

Wiking® technical fibers are supplied in tows or bales in textured form.

Dimensions

16 micron

Cut lengths

2-150 mm - cut lengths by appointment

Shortcut

2, 3, 4, 6, 12, 18, 19, 24 mm

In cable

By appointment.

Tow can be split and delivered by appointment.

All tows can be delivered in boxes by appointment.

All bales will be delivered with approx. 200 - 250 kg, depending on wish from customer.

Guarantee references

Wiking® Technical Fibres 16 micron, complies with EN-14.889-2, fibre class 1a, system 1 and is produced in an installation that is certified with ISO 9001-2004.

Danish Fibres strives for high quality but does not have control over all stages of the value chain. We therefore accept no responsibility for third-party production, customer processing, application, or the final result where our materials are used. All data is for guidance only, and the customer is responsible for assessing suitability for the intended purpose.

Health and safety

Please read the specific safety data sheets or contact the technicians at Danish Fibres.

Technical consultation

The technical department at Danish Fibres is available to you and can give advice about the correct use of our products.

It is always the user's responsibility to ensure the correct selection and application of Danish Fibres' products. This includes, but is not limited to, product selection, mixing, placement, design, manufacturing, and testing of materials in which the products are incorporated.

Danish Fibres provides general, non-binding information only, and has no control over third-party production, customer processing, application, or the final outcome where our materials are used. We therefore accept no responsibility for end products or for how our materials are used in practice.

Any losses or damages - direct or indirect - arising from incorrect use of information or products are the sole responsibility of the user. For further details, please refer to Danish Fibres' general terms and conditions of sale and delivery.